# artience

### **Rexta**™

Solvent Lamination Retort Ink

Toyo Ink America. LLC
An artience group company

1225 N. Michael Drive Wood Dale, IL 60191 USA Tel: 630-930-5100

www.artience-toyoinkamerica.com

### **Physical Characteristics**

- Very low solvent retention and odor.
- Swiss Ordinance compliant.
- Bond performance to an array of lamination structures.
- Sterilization, boil and Retort capable.
- Proven performance for applications that require resistance properties such as detergents.

#### Solvent Reducers:

- Standard: 85/15 N-Propyl Alcohol / N-Propyl Acetate
- Fast blend: 80/20 Ethyl Alcohol / N-Propyl Acetate
- Slow blend: 80/20 N-Propyl Alcohol / PM Acetate
- Slow reducers: Glycol PnB, Pnp, PE, use only as needed for print quality.

#### Structures:

- BOPP/ink/adh/BOPP
- BOPP/ink/adh/LLDPE
- PET/ink/adh/LLDPE
- BOPP/ink/adh/BOPP/AF
- BOPP/ink/adh/LLDPE/AF
- More specific structures can be requested by the TIA R&D center for ink properties and performance results.

#### Adhesives tested:

- Toyo-Morton TM219/CAT-10 & TM386/CAT-29BL
- Ashland Purelam™ A 9500 / B 9240
- Henkel LA 7660 / LA 6029
- H.B. Fuller WD4120 / WD4132

#### **Suggested Laminator Settings:**

- Adhesive coating weight should be 1.0 − 1.2 lb/rm, consistent across full web
- Nip roller temperature should be 120-130.
- Nip roller pressure should be around 40 psi, consistent across full web
- Assuring the adhesive to catalyst ratio is correct. Incorrect balance can cause issues with application, wet out, and lamination performance.
- Properties tested under controlled laboratory conditions.

#### **Press Conditions:**

Process Inks: 800 – 1000 LPI aniloxes
Press speeds: 600 fpm – 1000+ fpm

Web Pin-on temps:
 PP 130F – 140F, PET 165F – 175F

#### Ink Specifications:

- Shipping viscosity: 15-20 sec. #3 Signature Zahn
- Print viscosity-process inks: 24-30 sec. #2 Signature Zahn
- Ave.% Solids-Color= 30-45, Ave.% Solids-White= 55-70
- Shelf life: 12 months from manufactured date
- Ink Storage- 50F-100F in provided containers, out of direct sun.



## Toyo Ink America. LLC An artience group company

1225 N. Michael Drive Wood Dale, IL 60191 USA Tel: 630-930-5100 www.artience-toyoinkamerica.com

For technical assistance, call 1-979-778-1538.

All trademarks identified by the ® or ™ are registered trademarks or trademarks, respectively, of artience Co., Ltd or its subsidiary Toyo Ink America, LLC

Toyo Ink America, LLC. (TIA), an artience group member company, makes no claims or warranty regarding information contained within this document and disclaims all liability relating in any way to this information. All printing applications should be fully evaluated prior to press production. TIA recommends consultation with its technical experts and trials before general use of any product. For more information, please consult your account manager. For technical questions, please contact your local TIA lab manager or field service technician.