

ORIBAIN BTX-673

1. Features

BTX-673 is one component hardening type of acrylic resin solution.

2. Specification

Subjects	BTX-673
Appearance	Light-yellowish transparent viscous liquid
Solid content	48.0 ± 1.0 %
Viscosity	4500 ± 1500 mPa·s
Solvent	Ethyl acetate, Methyl ethyl ketone, Toluene, IPA

3. Usage Instructions

Coating weight: 65 g/m² (as dry)

Dry up: 105 °C for 2 min

4. Performance

Standard Determination

Subjects	BTX-673			UL 181 SPEC
	Coating weight: 65 g/m ² (as dry)			
180° Peeling strength at 23°C50%RH (lb/inch)	to SS	15min dwell	4.00	>3.75 (>60 oz/inch)
		24hrs dwell	4.38	—
Shear (mm)	to SS	65°C-5lbs-6hrs	Pass	Pass
		R.T.-10lbs-120hrs	Pass	Pass

Base material : Commercially available 2mil Aluminum Foil

Liner : Commercially available laminated release liner paper.

5. Handling and Storage

- Storage : Store this product in the warehouse for dangerous products.
Protect this product from high temperature and direct sunlight.
- Handling : Do not handle or store near an open flame, sources of heat or
sources of ignition.
: Keep container closed. Use only in the well-ventilated areas and
wear proper protection equipment to avoid skin contact and vapor
inhalation.

* The general description, recommended uses, application data and statements in the product literature and label are guidelines only. Users should test this product in advance to verify suitability for particular uses.